

12V65AH

CE



Features:

- ▲ Maintenance-free operation
- ▲ Stable quality and high reliability
- ▲ Compact design
- ▲ 10 years design time (at 25° C)

Applications:

- ♦ UPS
- ★ Emergency lighting
- ▲ Solar panel system
- ▲ Alarm and security system
- \clubsuit Telecommunication system

- ♠ Fire alarm and security systems
- ◆ DC power supply Auto control system
- ♠ Backup power for testing and measuring instruments
- ♠ Electronic apparatus and equipment Communication power supply
- ♠ etc

Specifications:

Туре	Specification					
Nominal Voltage	12v(6cells)					
	65ah (20hrs, 25℃/77°F)					
Nominal Capacity	56ah (5hrs, 25℃/77°F)					
	39ah (1hrs, 25℃/77°F)					
	Length: 350±2mm					
Dimension	Width: 167±2mm					
Dimension	Container Height: 175±2mm					
	Total Height(with Terminal):175±3mm					
Approx Weight	20.5kg					
Terminal	T3 or F5					
Container material	ABS					
Max.Discharge Current	700A(5s)					
Internal Resistance	Approx 6.8mΩ					
	Discharge:-15-50°C(5-122°F)					
Operation Temp.Range	Charge: 0-40°C (32-104°F)					
	Storage: -15-40 °C (5-104 °F)					
Nominal Operating Temp.Range	25±3°C(77±5°F)					
Cycle Use	14.4V-14.8V(25°C/77°F) Coefficient:30mv/ °C (Initial charging current less than 16.5A)					
Standby Use	13.5V-13.8V(25℃/77°F) Coefficient:20mv/ ℃ (No limit on Initial Charging Current)					
	103% 40°C(104°F)					
Capacity affected by Temp.	100% 25°C(77°F)					
	86% 0℃(32°F)					


Self Discharge:

KANGLIDA batteries maybe stored for up to 6months at 25°C (77°F) and then a freshing charge is required, for higher temperatures the time interval will be shorter.

F.V/Time	10min	15min	30min	45min	1h	2h	3h	5h	10h	20h
r.vi i inte	TVIIIII	1 JIIIII	JUIIII	40000	,100,	211	SII	JI	TUN	2011
1.80V/cell	116	95	59	45.5	37.1	21.6	16.3	11.2	6.6	3.38
1.70V/cell	137	111	64	48.8	39.3	22.9	17.0	11.6	6.7	3.48
1.60V/cell	153	123	70	52.7	42.3	24.2	17.8	12.0	6.8	3.58
		Cor	nstant Pov	wer Discha	arge(Watt	s per cell	at 25°C/77	°F)		
F.V/Time	10min	Cor 15min	nstant Pov 30min	wer Discha 45min	arge(Watt 1h	s per cell 2h	at 25°C/77 3h	°F) 5h	10h	20h
F.V/Time 1.80V/cell	10min 213								10h 13.0	20h 6.69
		15min	30min	45min	1h	2h	3h	5h		


Note: the above characteristics data are average values obtained within three charge/discharge cycles, not the minimum values.


Dimensions:





Characteristics:


Charge characteristic Curve for standby use











Maintenances and Attentions:

1. After received product, please checked box damaged or not, if find crack on battery body, contact with us and logistics, it should be caused by boorish handle during delivery;

2.Don't pull or shake terminal, otherwise, it may cause terminal loosen;

3.Battery is not allowed close to Tepid source or basked under the sun for a long time;

4. Charge in the obturate container is not allowed;

5.No short circuit. Battery should be stored full of electronic when not in need, and the battery should be charged every three months in order to avoid the irreversible sulphation. When battery case bursts or electrolyte leaks, battery should be changed lest the acid corrosion.

6.No battery in environment with the acid gas.

7.When battery is used as the backup battery, be careful and check it at regular time to avoid the damage battery. Especially the battery beyond one year should be checked in time, and change the less capacity and scrapped battery. (some batteries maybe have voltage but no current; some batteries maybe have current but no voltage; some maybe have both but less capacity:all these conditions cannot meet the work, reach the power-on time. Do not forth small battery, cause the huge losses)

8. Forbidden put battery in the fire, otherwise it will cause an explosion.

9.When battery cracks or leaks, please use cotton cloth clean it. When skin contacts to the liquid, wash with fresh water immediately. See doctor if serious. 10.No wash on the surface of the battery with the organic solution.